




## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup>:</b> A61L 27/00, A61C 8/00, C23C 24/04, C21D 7/06, B24C 11/00	<b>A1</b>	<b>(11) International Publication Number:</b> WO 95/13102 <b>(43) International Publication Date:</b> 18 May 1995 (18.05.95)
<b>(21) International Application Number:</b> PCT/US94/12581 <b>(22) International Filing Date:</b> 3 November 1994 (03.11.94) <b>(30) Priority Data:</b> 08/149,905 10 November 1993 (10.11.93) US <b>(71) Applicant:</b> IMPLANT INNOVATIONS, INC. [US/US]; 3071 Continental Drive, West Palm Beach, FL 33407 (US). <b>(72) Inventor:</b> BEATY, Keith, D.; 245 Miramar Way, West Palm Beach, FL 33405 (US). <b>(74) Agent:</b> RUDISILL, Stephen, G.; Arnold, White & Durkee, P.O. Box 4433, Houston, TX 77210 (US).		<b>(81) Designated States:</b> AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LT, LU, LV, MD, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ).  <b>Published</b> <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> SURGICALLY IMPLANTABLE PROSTHETIC DEVICES    <b>(57) Abstract</b>  The surface of a surgically-implantable prosthetic device is impacted with particles of the same material as the device to form the surface into a desired pattern of roughness.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Larvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

## **SURGICALLY IMPLANTABLE PROSTHETIC DEVICES**

### **Introduction**

The success of prosthetic devices surgically implanted in living bone depends entirely on achieving an enduring bond between the confronting surfaces of the device and the host bone. A surgical procedure for preparing living bone to receive a surgically implanted prosthetic device has been known for twenty years or more, but considerable controversy remains concerning the ideal properties of the surface of the implanted device which confronts the host bone. This invention relates to processes for improving those surfaces of the prosthetic devices and to devices having the improved surfaces, so as to enhance the quality and durability of bonding between the prosthetic devices and the host bone.

### **BACKGROUND**

It is known through clinical experience extending over several decades that titanium and its dilute alloys have requisite biocompatibility with living bone to be acceptable materials for use in making surgically implantable prosthetic devices when the site of installation is properly prepared to receive them. There is, however, less certainty about the ideal physical properties of the surfaces of the prosthetic devices which confront the host bone.

Accordingly, at the present time, owing to its predictable success, the endosseous dental implant fixture made of titanium is the artificial root most frequently chosen for restoring dentition to edentulous patients. However, that success depends in part on the micromorphologic nature of the surface of the implant fixture which comes in contact with the host bone. The response of cells and tissues at implant interfaces can be affected by surface topography or geometry on a macroscopic basis as well as by surface morphology or roughness on a microscopic basis.

Because there is no standard for surface micromorphology of dental implants, the surfaces of commercial implants have a wide range of available textures. Up to now, it is known that osseointegration of dental implants is dependent, in part, on the attachment and spreading of osteoblast-like cells on the implant surface, and it appears that such cells will attach more readily to rough surfaces than to smooth

surfaces, but an optimum surface has yet to be defined. Buser, D. et al "Influence of surface characteristics on bone integration of titanium implants. A histomorphometric study in miniature pigs" Journal of Biomedical Materials Research, Vol. 25, 889-902(1992).

5 It has been suggested by some that the ideal surface will have pits that have very small dimensions in the nanometer range, and by others that bone growth into a porous surface coat of Ti6AlV4 alloy with pore size between 50 and 150 micrometers is an efficient and rapid means of bonding endosseous dental implants in humans. Buser et al (Ibid) clearly showed that the extent of bone/implant interface is positively  
10 correlated with increasing roughness of the implant surface.

Mention of implant topography, or texture, occurs frequently in the literature and patents relating to this subject; for example, U.S. Patent No. 4,180,910 issued to F. Straumann et al, January 1, 1980, at column 2, lines 59 to 67 describes a dental  
15 implant member made of titanium provided with a coating of titanium granules applied to it by flame spraying, producing a rough surface "comprising pores, most of which have a diameter of 1 to 10um, although still smaller pores are also present". Similar results are reported in a published article emanating from the University of Bern (Switzerland), Clinic for Dental Maintenance (Schweizerische Monatschrift fur Zahnheilkunde, Vol. 86, No. 7, July 1976, pp. 713-727). U.S. patent No. 3,855,638  
20 issued to Robert M. Pilliar December 24, 1974 discloses a surgical prosthetic device made of a body of a selected material and having on its surface a layer of particles of the same material forming a porous coat of the particles. It has been suggested, e.g.: PCT application No. SE91/00672, International Publication No. W092/05745 and date April 16, 1992, to blast the surface of implants of titanium or an alloy of  
25 titanium with particles of a titanium oxide.

Prior-known processes for achieving biocompatible surfaces on surgically implantable prosthetic devices have taken many forms, classifiable primarily as:

1 - processes which add something to the surface; and

2 - processes which take something away from the surface.

30 Among the first class are coating, cladding and plating processes, which include, as examples, the processes described in the above-mentioned patents to Straumann et al, and to Pilliar, and processes which coat a body with bone-compatible apatite

materials, such as hydroxyapatite or whitlockite. The latter has spawned a vast literature which includes U.S. Patent No. 4,818,559 issued to Hama et al. April 4, 1989. Among the second class are acid etching, ion etching, chemical milling, laser etching and spark erosion. Sometimes processes of both classes are combined, as in  
5 the Hama et. al. patent.

It is well understood that the chemical properties of the surfaces of surgically implantable prosthetic devices should as much as possible exclude impurities which could lessen the biocompatibility of the devices. See, Ibid, Pilliar and PCT publication No. WO92/05745. Thus, for example, traces of elements of the tools  
10 used to turn titanium in a lathe may become embedded in the surface of a device, contaminating the device notwithstanding that the starting piece of titanium may have been "pure" to the governing specification of biocompatibility.

It has been suggested that the type of roughness produced on a chemically pure titanium surface does affect initial biological responses such as cellular  
15 attachment and spreading. An irregular rough surface produced by sand blasting appears to be more conducive to cellular attachment than other rough surfaces produced by polishing/grinding or acid etching. (Int. J Oral Maxillofacial Implants 1992;7: 302-310)

P. Ducheyne et al, "The Effect of Hydroxyapatite Impregnation on Skeletal  
20 Bonding of Porous Coated Implants" J. Biomed. Mater. Res. 14,225-237 (1980) describe a cylindrical plug of stainless steel coated with a porous metal fiber of the same material, with the individual fibers lined with hydroxyapatite, for increasing the rate of bone in growth when implanted in the femur of living dogs.

S.D.Cook et al, "Torsional Stability of HA Coated and Grit-Blasted Titanium  
25 Dental Implants" J. Oral Implantat. 18(4)pp 354-65 (1992), in a comparative study in dogs, showed superior interface torsional strength for the HA-coated implants, with interface failure seen to occur primarily at the HA/implant interface.

The present invention is not based essentially on addition to or taking away from the surface of the prosthetic device. While it may fit incidentally into the  
30 second class, and in some embodiments it may appropriate properties of the first class, it is primarily concerned with reforming the surface without necessarily removing any material from it or adding any material to it. The invention

accordingly addresses new and greatly improved processes for achieving a biocompatible surface on surgically-implantable devices wherein the existing surface is selectively and controllably manipulated to form a new prescribed surface topography or texture.

5    General Nature of the Invention

It is a general object of the present invention to produce an improved surgically implantable prosthetic device having on its surface a prescribed micromorphology; another object is to produce such a device having on its surface a controllably-prescribed distribution of indentations in the form of pits, dents,  
10 scratches and/or craters with dimensions in a controllably-prescribed range.

It is an additional object of the invention to produce an improved surgically implantable device of the type described without contaminating the surface of the device.

A further object of the invention is to teach a process or processes for making  
15 the improved device.

According to the invention in one of its more general aspects the surface of a surgically implantable prosthetic device is impacted with particles of a material which is related to the material of the device and preferably harder, e.g: an alloy of that material, in order to form the desired micromorphology without risk of contaminating  
20 that surface. For example, a titanium body is impacted with a titanium grit which is not required to remain on the surface. The relative hardness, the quantities, sizes and shapes, of the grit particles, and the impact-velocity of the particles and the direction of their impact, are each selected and controlled with a view to the size, shape, character and distribution of the surface depressions or indentations intended  
25 to be formed. Thus, the invention envisions controllably forming surface depressions that are round or elongated (e.g: oval) in shape, that have smooth or sharp-edges contours, that are simple dents or scratches in the surface, or that are crater-like with a berm surrounding or partly surrounding the depression. The particles in the grit preferably have greater hardness than the body of the device. For example, if the  
30 device is made of pure titanium the grit particles may be of a dilute alloy that is harder. The grit may be carried in a fluid in which the concentration of the particles may be controlled and the particles may be directed in a stream to achieve a desired

distribution and array-pattern of indentations or depressions on the surface of the device.

The grit may include particles of a bone-compatible apatite material, such as hydroxyapatite or whitlockite, some of which are deliberately embedded in the surface of the titanium body by the process of the invention. In a particular embodiment of the invention, the grit may be predominantly or even entirely composed of the apatite material. Such embodiments, unlike prior devices coated with the known coatings, resist separation of the apatite material from the titanium body when the prosthetic device is put into use.

Processes for making the invention include steps for forming, selectively, each form of depression in the surface of the device, under controllable conditions. Such steps include, as one example, preparing a fluidized bed of grit particles in which the hardness, shapes, sizes, compositions and concentrations of the particles can be precisely controlled and directing a stream of the fluid bearing the particles under controlled velocity and direction toward the surface of the device. In another embodiment the process includes the steps of providing the grit particles in a whirling cyclonic fluid and locating the device in the whirling fluid while slowly turning it to expose its surface to impact by the particles. The carrier fluid may be a gas or a liquid. The particles may be propelled without a carrier. Heat is not necessary to the process.

The invention has the ability to provide surface treatments for surgically implantable prosthetic devices which can be tailored to the advances in clinical knowledge which are occurring and will continue to occur in the future. It has the further ability to provide a prescribed surface micromorphology for clinical research and investigation designed to elucidate paths leading to such advances; thus, the invention has as a further and very important object the advancement of progress in the design of surgically implantable prosthetic devices.

That titanium particles may have surface layers of naturally-forming oxides of titanium, to a thickness of perhaps 80 Angstrom units, is not material to the invention. The invention does not require the presence of any oxide(s), and is fully functional without them.

Implant devices with surfaces selectively prepared according to the present

invention may be subjected to an additional process according to U.S. Patent No. 5,188,800, owned by the Assignee of the present application, so as to increase wettability of the surface. That additional process involves placing the implant in a plasma cleaning device, therein subjecting the implant to a flow of substantially pure gas (e.g. an inert gas selected from Krypton, Argon, and mixtures thereof; or oxygen), continually removing gas from the plasma cleaning device so as to maintain a vacuum therein in the range about 20 to about 5,000 microns, and continuing the flow and the vacuum for a period of time to clean and sterilize the implant and until the surface develops a surface contact angle of about 20 degrees or less, preferably about 10 degrees or less, and more preferably about 5 degrees or less. The disclosure of said patent No. 5,188,800 is incorporated herein by reference.

#### **Description of Exemplary Embodiments of the Invention**

The invention will be more fully explained in the following description of exemplary embodiments with the aid of the accompanying drawings, in which:

FIG. 1 schematically illustrates a surface modified to have a depression surrounded by a berm;

FIG. 2 shows a means to modify a surface with a projectile aimed to impact the surface normally;

FIG. 3 schematically illustrates a surface modified to have a depression without a berm;

FIG. 4B is a top view schematically illustrating a surface modified to have a non-symmetrical depression partly surrounded by a non-symmetrical berm;

FIG. 4A is a section on line X-X of FIG. 4B;

FIG. 5 shows a means to modify a surface with a projectile aimed to impact the surface obliquely;

FIG. 6 shows a scheme for impacting a surface with a stream of projectiles aimed to impact the surface substantially normally;

FIG. 6A schematically shows a partial plan view of FIG. 6;

FIG. 7 shows a scheme for impacting a surface with a stream of projectiles aimed to impact the surface obliquely;

FIG. 8 shows a scheme for impacting a surface in a cloud of projectiles generated in a fluidized bed; and



FIGS. 9A and 9B are photocopies of two photographs showing a dental implant surface - modified according to the invention.

In FIGS. 1 and 2 a segment of an article 10, which article may be a dental implant fixture, has an outer surface 12 which has been modified (FIG. 1) to have a depression 14 surrounded by a berm 16. The depression has substantially round perimeter and the berm is substantially symmetrical around that perimeter. This depression may be formed by impacting the surface 12 with a projectile 18 aimed to hit the surface normally, as is represented by the arrow 20 in FIG. 2. Depending on the velocity of the projectile on impact the depression may have the berm 12, or it may be without a berm as is illustrated in FIG. 3. The mass of the projectile, its hardness, its velocity on impact, its surface characteristics and its shape will all combine to determine the characteristics of the depression, such as its shape and depth.

FIGS. 4 and 5 shows a non-symmetrical depression 24 (FIG. 4) in the surface 12, formed by impacting the surface with the projectile 18 aimed to impact the surface at an oblique angle as is represented by the arrow 26 in FIG. 5. The depression may have a non-symmetrical berm 28, or not, depending on the above-mentioned properties of the projectile.

A stream 29 of projectiles 18 may be aimed to impact the surface 32 of a cylindrical body 30 substantially normally using the scheme shown in FIG. 6. A mask 34 fitted with a slot 36 is placed adjacent the surface 32 in the path of the stream of projectiles, so that those projectiles which pass through the slot will impact the surface 32 substantially normally. The slot 36 has a length at least as great as the axial length of the body 30, as is represented in FIG. 6A, so that projectiles 18 may impact the surface 32 along its entire length. The body 30 may be rotated on its axis A, counterclockwise as represented by the curved arrow B, or vice versa, to expose the entire surface 32 to projectiles 18. The number of depressions formed on the surface 32 will depend primarily on the density of projectiles in the stream and the speed of rotation of the body.

The stream of projectiles may be aimed obliquely, or tangentially, at the surface 32 using the scheme shown in FIG. 7. The character of the pits formed in this manner will depend, additionally, on the direction of rotation of the body 30.

In FIG. 8 a fluidized bed 40 provides a cloud of particles 18 in the confined space 42 above the bed. Several articles (e.g: dental implants) 30 are in that space, each mounted to a support 44 for rotation around its longitudinal axis A-A. The density of this cloud and the velocity of individual particles in it are established as desired to effect the required modification of the surfaces of the articles 30. By this means a uniform pattern of depressions may be produced on the surface of each article.

In another scheme, the implant is located in a whirling cyclonic stream of particles 18 (not shown), where it may be rotated to expose its entire surface to oncoming particles. In this scheme, as in the others described and illustrated herein, prolonged exposure of the implant surface will result in an overlapping mass of irregularities to the point of destroying features of individual impressions, dents, scratches and the like.

To add a bone-growth promoting agent to a surface that has been modified according to the invention one may substitute particles of that agent for some or all of the surface-modifying projectiles 18 in any of the above-described processes and apparatus. Thus, for example, one may add particles of hydroxy-apatite, whitlockite or another agent, such as a carrier for a medicament (e.g: a bone morphogenic protein), to the particles 18 of titanium or its alloy, or substitute same after the implant surface has been modified, and continue the process to place particles of the bone-growth promoting agent in the depressions formed on that surface. If the implant surface has non-symmetrical depressions 24 or the like, as illustrated in FIGS. 4A and 4B, for example, the bone-growth promoting agent can be projected into those depressions while the implant 30 is being rotated clockwise, for example, as seen in FIG. 7. If, further, the implant is designed to be screwed into the patient's bone socket with a clockwise rotation, small chips of bone will be gathered into the depressions, and be packed therein on top of the growth-promoting agent. The invention envisions such an embodiment of the invention, which will inherently resist separation of the growth-promoting agent from the implant surface 12, thereby overcoming a problem which is indigenous to the prior art.

The shape of the particles 18 etc may be controlled with the aid of fluidized

bed apparatus of the kind illustrated in FIG. 8. If initially particles in the cloud are rough-shaped with sharp edges, corners and the like, one may maintain the cloud for an extended time interval during which the particles in the cloud will impact each other smoothing away the sharp corners and edges. Particles which are substantially round may be produced in this way, in order to form substantially round depressions on the surfaces of the articles 30. If the article 30 is made of c.p.titanium and it is desired to use projectiles which are harder than the article 30, the projectiles may be made of the alloy TiAl6V4.

The apparatus and processes illustrated in the drawings are exemplary. Other methods and means to impact particles on a surface, which may be used in practicing the present invention, are mentioned in the above-references PCT Application, for example.

An example of a dental implant surface modified according to the invention is shown in FIGS. 9A and 9B. FIG. 9A is a 50x photographic enlargement of a portion of a screw-type dental implant only part of the surface of which has been modified. The unmodified part 102 is the threaded surface produced by machine turning of a billet of titanium. The modified part 104 was impacted with a Ti6AlV4 grit (-325 mesh) sprayed at 90 degrees substantially normal to the surface at pressure = 70PSI (indicated on the photograph) for approximately 3-5 minutes while the implant was rotated at an angular speed of about 10 seconds per revolution. The array of dots at the lower right of FIG. 9A measures 0.60mm in the axial direction of the implant. FIG. 9B is a further enlarged view looking along the modified surface 104. As is apparent in these figures the implant procedure was continued long enough to substantially obliterate features of individual depressions, dents, scratches and the like, so as to produce an intense, substantially uniform roughness of the bone-contacting surface of the implant. It has been observed that individual depressions and dents, will have transverse dimensions (e.g: diameters) about half the size of the impacting grit particles. Thus, a grit of -325 mesh, having particles in the size range from about 10-15 microns, will generally produce depressions about 5-10 microns across at the surface of the implant.

**WHAT I CLAIM IS:**

1. Method for enhancing biological responses to a device that is surgically implantable in living bone comprising the steps of providing an implantable body of a biocompatible material having a surface for interfacing with said bone, and impacting said surface with a grit made essentially of particles of substantially the same material so as to reform said surface to a prescribed micromorphology.
2. Method according to claim 1 carried out without substantially adding material to or removing material from said body.
3. Method according to claim 1 in which said grit includes particles of a bone-growth-enhancing material.
4. Method according to claim 3 in which said grit includes a carrier for a medicament including without limitation a bone morphogenic protein..
5. Method according to claim 1 in which said body is made of a material selected from titanium and its dilute alloys, and said grit is made of a material selected from titanium and its dilute alloys.
6. Method according to claim 5 in which said body is made of chemically-pure titanium and said grit is made of TiAl6V4.
7. Method according to claim 1 in which said grit is selected to consist primarily of particles in the size range from 10 to 15 microns, (-325 mesh).
8. Method according to claim 1 including the steps of dispersing said particles of said grit in a fluid and moving said fluid to carry said grit to said surface.
9. Method according to claim 8 including the step of moving said fluid with a pressure in the range from 60 to 80 psi.
10. Method according to claim 1 including the step of treating said reformed surface to have a surface contact angle of about 20 degrees or less.
11. Method according to claim 1 in which said grit is selected to consist primarily of particles which are substantially devoid of sharp points or edges.
12. Method according to claim 1 in which said grit is selected to consist primarily of particles which have substantially sharp topographical features selected from edges and points.

13. Method according to claim 1 carried out substantially in the absence of oxygen.

14. Method according to claim 1 including the step directing said particles at a prescribed angle to said surface.

15. Method according to claim 14 including the step of choosing said angle to be in a range from about normal to said surface to about tangent to said surface.

16. Method according to claim 15 including the step of choosing said angle to be in the range toward normal to said surface so as to form predominantly substantially round depressions in said surface.

17. Method according to claim 16 including the step of choosing a density of said particles in a range that will form predominantly discrete depressions in said surface.

18. Method according to claim 16 including the step of choosing a velocity of said particles that will form predominantly discrete craters in said surface.

19. Method according to claim 15 including the step of choosing said angle to be in the range toward tangent to said surface so as to form predominantly substantially elongated depressions in said surface.

20. Method according to claim 1 including the steps of choosing a range of particle velocity and a range of particle density that will form in said surface a variety of irregularities substantially overlapping each other.

21. Method according to claim 1 including the steps of directing said particles into a cyclonic path and locating said implantable body in said path.

22. Method according to claim 21 including the step of rotating said body in said path so as to expose said surface substantially entirely to impaction by said particles.

23. Method according to claim 1 including the step of providing an aperture mask over said surface for restricting the angle of incidence of said particles on said surface to a prescribed range within the limits of predominantly normal to predominantly tangential.

24. Method according to claim 3 which includes the step of embedding in said surface some of said particles of a bone-growth-enhancing material.

25. Method according to claim 1 including the steps of providing a fluidized cloud of said particles and locating said device in said cloud.

26. Method according to claim 25 including the step of rotating said device in said cloud.

27. A prosthetic device surgically implantable in living bone, said device having a surface of a biocompatible material for confronting said bone, said surface being formed by impaction with a similar material to a prescribed pattern of irregularities selected from among depressions, scratches and dents of prescribed sizes and configurations.

28. A prosthetic device according to claim 27 in which said irregularities substantially overlap each other.

29. A prosthetic device according to claim 27 including particles of a second biocompatible material substantially fixed in said irregularities.

30. A prosthetic device according to claim 27 in which each of said materials is selected from titanium and its dilute alloys.

31. A prosthetic device according to claim 27 in which said first material is selected from titanium and its dilute alloys and said second material includes particles selected from a bone-compatible apatite and a carrier of a medicament including without limitation a bone morphogenic protein.

32. A prosthetic device according to claim 27 in which at least some of said depressions have peripheral berms.

33. A prosthetic device according to claim 27 in which substantially all of said irregularities are dents.

34. A prosthetic device according to claim 33 in which at least some of said dents have peripheral berms.

35. A prosthetic device according to claim 27 in which said irregularities are formed by ball-like particles of substantially the same material impacting said surface at a prescribed angle ranging from substantially perpendicular to said surface to substantially tangent to said surface.

36. A prosthetic device according to claim 35 in which said ball-like particles are harder than said biocompatible material.

37. A substantially cylindrical dental implant having on its surface depressions elongated in the circumferential direction with their openings oriented forward toward the direction in which the implant is turned to install it in a receiving bore in a patient's jawbone, for receiving into said depressions chips of said bone when said implant is turned in said bore.

38. An implant according to claim 37 including bone-growth-enhancing material in at least some of said depressions, positioned to be retained in said depressions by said chips when the latter are received therein.

39. An implant according to claim 37 in which at least some of said depressions have berms partially surrounding the rearward boundaries of said openings.

40. An implant according to claim 38 in which said bone-growth-enhancing material is selected from among hydroxyapatite materials, whitlockite materials, and medicaments including without limitation bone morphogenic protein.

41. An implant according to claim 37 in which the smaller dimensions of said openings range in size from about 5 microns to about 10 microns.

42. An implant according to claim 37 having a surface contact angle of about 20 degrees or less.

43. A prosthetic device according to claim 27 having a surface contact angle of about 20 degrees or less.

44. Method according to claim 1 comprising the further step of contacting said surface with one or more other materials for enhancing osseointegration selected from among apatite materials, carriers for medicaments and bone morphogenic proteins.

45. Method according to claim 44 in which said further step comprises impacting said surface with particles of at least one of said materials.

46. Method according to claim 45 in which said particles are selected to be a carrier for a medicament.

47. Method according to claim 45 in which said particles are selected to be a carrier for a bone morphogenic protein.

48. Method according to claim 45 in which said particles are selected to be of

hydroxyapatite or whitlockite.

49. Method for enhancing mechanical retention of a device that is surgically implantable in living bone comprising the steps of providing an implantable body of a biocompatible material having a surface for interfacing with said bone, impacting said surface with essentially a material capable of reforming said surface, and controlling said impacting so as to reform said surface to a prescribed micromorphology.

50. Method according to claim 49 in which said material is selected to include one or more of

- a- substantially the same material as said body
- b- a bone-growth-enhancing material
- c- a carrier for a medicament
- d- hydroxyapatite
- e- whitlockite
- f- a bone morphogenic protein
- g- a grit of any one or more of the foregoing.

51. Method according to claim 50 including the steps of impacting said surface with first one and then another of said materials, *seriatim*.

52. Method according to claim 50 including the steps of impacting said surface with a grit of first one and then another of said materials, *seriatim*.

53. Method according to claim 50 including the steps of impacting said surface with a grit of substantially the same material as said body, followed by impacting said surface with a grit of a bone-growth-enhancing material.

54. Method according to claim 50 including the steps of impacting said surface with a grit of substantially the same material as said body, followed by impacting said surface with a grit of a material selected from hydroxyapatite and whitlockite.

55. Method according to claim 50 including the steps of impacting said surface with a grit of substantially the same material as said body, followed by treating said surface with a carrier for a medicament.

56. Method according to claim 50 including the steps of impacting said surface with a grit of substantially the same material as said body, followed by



treating said surface with a bone-morphogenic protein.

57. Method according to claim 50 including the steps of impacting said surface with a grit of substantially the same material as said body, followed by impacting said surface with a grit of a carrier for a medicament.

58. Method according to claim 50 including the steps of impacting said surface with a grit of substantially the same material as said body, followed by impacting said surface with a grit of a carrier for a bone-morphogenic protein.

59. Method according to claim 50 comprising the step of impacting said surface with a grit of hydroxyapatite.

60. Method according to claim 59 including the further step of treating said surface with a bone-morphogenic protein.

61. Method according to claim 59 including the further step of impacting said surface with a grit of a carrier for a bone-morphogenic protein.




FIG. 1




FIG. 2




FIG. 3




FIG. 4A




FIG. 4B




FIG. 5




FIG. 6




FIG. 6A




FIG. 7





FIG. 8


Ti/Ti6-46B-70PSI-Y

FIG. 9A



Ti/Ti6-46B-70PSI-Y

FIG. 9B



# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US 94/12581

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 A61L27/00 A61C8/00 C23C24/04 C21D7/06 B24C11/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A61L A61C C23C C21D B24C A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO,A,92 05745 (ASTRA AB ) 16 April 1992 cited in the application see page 3, line 16 - line 34; claims; examples	1-27
A	US,A,4 818 559 (HAMA MASAOKI ET AL) 4 April 1989 cited in the application see column 2, line 55 - column 3, line 60; claims; examples	44, 45, 48-54
A	EP,A,0 213 836 (CANON KK ) 11 March 1987 see column 5, line 26 - line 46; claims; figures	1, 2, 7, 12, 16-18
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*&\* document member of the same patent family

Date of the actual completion of the international search

28 February 1995

Date of mailing of the international search report

16.03.95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+31-70) 340-3016

Authorized officer

Cousins-Van Steen, G

# INTERNATIONAL SEARCH REPORT

Inter. Natl Application No  
PCT/US 94/12581

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 409 810 (ELLEM BIOTEKNIK AB ) 23 January 1991 see claims -----	3,4,47, 60



# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 94/12581

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
WO-A-9205745	16-04-92	SE-B-	468153	16-11-92
		AU-B-	647192	17-03-94
		AU-A-	8663691	28-04-92
		CA-A-	2093517	09-04-92
		EP-A-	0552261	28-07-93
		JP-T-	6502555	24-03-94
		SE-A-	9003206	09-04-92
-----				
US-A-4818559	04-04-89	JP-A-	62034558	14-02-87
		JP-A-	62034559	14-02-87
		EP-A, B	0212929	04-03-87
-----				
EP-A-0213836	11-03-87	JP-C-	1717759	14-12-92
		JP-B-	4003867	24-01-92
		JP-A-	62036676	17-02-87
		DE-A-	3688411	17-06-93
		DE-T-	3688411	28-10-93
		EP-A-	0525918	03-02-93
		US-A-	4939057	03-07-90
		US-A-	5009974	23-04-91
-----				
EP-A-0409810	23-01-91	SE-B-	464850	24-06-91
		CA-A-	2021473	20-01-91
		JP-A-	3070566	26-03-91
		JP-B-	6004089	19-01-94
		SE-A-	8902565	20-01-91
		US-A-	5152993	06-10-92
-----				